Versastique™

by penreco®

Clear Soothing Sunscreen Stick

Versastique™ by penreco

138 Petrolia St. Karns City, PA 16041
Phone: 800-245-3952 or 724-756-0110 Fax: 724-756-1050
Email: penreco@clmt.com Web: www.penreco.com/versastique

Clear Soothing Sunscreen Stick

PRODUCTS

Raw Material	Composition	% w/w	Supplier
PHASE 1			
Versastique Clear ME 5T	Hydrogenated Polyisobutene, Butyl Stearate, Isostearyl Alcohol, Hydrogenated Styrene/Butadiene Copolymer, Octyl Dodecanol, Dibutyl Lauroyl Glutamide, Dibutyl Ethylhexanoyl Glutamide, Pentaerythrityl Tetra-Di-t-Butyl Hydroxyhydrocinnamate	78.00	Penreco
PHASE 2			
Avobenzone	Butyl Methoxydibenzoylmethane	3.00	DSM
Homosalate	Homosalate	10.00	DSM
Octyl Salicylate	Ethylhexyl Salicylate	5.00	DSM
Octocrylene	Octocrylene	4.00	DSM

MAKING PROCEDURE:

Heat Phase 1 until completely dissolved (120 - 130 °C). Start stirring and allow to cool to 115 °C. Add Avobenzone and stir until dissolved. Add the rest of Phase 2 ingredients sequentially with continued stirring. Continue stirring at 115 °C for 1 hour. Pour into desired packaging.

© 2019 Calumet Specialty Products Partners, L.P. Rev 09.19