



Nude Stick Foundation

The foundation has never been so easy and fun to apply! Ideal for the whole face or for simple touch-ups, its compact size allows you to keep it always close at hand. It ensures a nude finish and a long lasting effect with an amazing powdery feel.



Nude Stick Foundation

PRODUCTS

Raw Material	Composition	% w/w	Supplier
PHASE A			
Versastique™ ME40T	Hydrogenated Polyisobutene, Butyl Stearate, Isostearyl Alcohol, Butylene/Ethylene/Styrene Copolymer, Ethylene/Propylene/Styrene Copolymer, Dibutyl Lauroyl Glutamide, Pentaerytrityl Tetra-Di-T-Butyl Hydroxyhydrocinnamate	21.00	Penreco
Versagel® MC 1600	Isohexadecane, Ethylene/Propylene/Styrene Copolymer, Butylene/Ethylene/Styrene Copolymer	6.20	Penreco
Versagel® MG 750 T	Hydrogenated Poly(C6-14 Olefin), Ethylene/Propylene/Styrene Copolymer, Butylene/Ethylene/Styrene Copolymer, Pentaerythrityl Tetra-Di-T-Butyl Hydroxyhydrocinnamate	4.00	Penreco
Cetearyl Alcohol	Cetearyl Alcohol	13.00	

PHASE B

Mackaderm Lia	Isoamyl Laurate	8.50	Solvay
Cetearyl Ethylhexanoate	Cetearyl Ethylhexanoate	4.00	
Geogard® LSA	Butylene Glycol, Benzyl Alcohol, Sorbic Acid, Caprylic/Capric Triglyceride, Lauryl Alcohol, Myristyl Alcohol	1.00	Lonza

PHASE C

Mixed ground pigment blend	Titanium Dioxide, HDI/trimethylol Hexyllactone crosspolymer, talc, Silica, C.I. 77491, C.I. 77492, C.I. 77499; Dimethicone, Triethoxycaprylsilane	15.00	
Agenaflo 9052	Aluminium Starch Octenylsuccinate	9.00	Agrana
Rice Po 4 Natural	Distarch Phosphate	18.00	Agrana
Prof. Rose Mist 236	Parfum	0.30	IFF

MIXING INSTRUCTIONS

Mix phase A, heating to 90-95°C, until clear liquid, then allow to cool.
 When phase A is at 75°C, add phase B, mixing until homogenous, then cool to 50°C.
 Add phase C, mixing until homogenous.